





Nickel alloy 2.4668/Alloy 718

The material 2.4668/Alloy 718 is a corrosion resistant high strength nickel-based super alloy. The presence of higher concentrations of Molybdenum and chromium the material exhibits excellent corrosion and oxidation resistance even at elevated temperatures. The material 2.4668 is heat treatable and this makes the material to be customized for various applications.

Properties

- High strength and
- toughness
- Good corrosion and
- oxidation resistance
- Good processability
- Good creep resistance

Applications


- Aviation and Aerospace
- Energy industry
- Casting industry
- Automotive industry



Powder properties

Chemical Composition (wt.-%)

| Element | Min. | Max. | | |
|---------|----------|------|--|--|
| С | <0.08 | | | |
| Si | <0.35 | | | |
| Mn | <0.35 | | | |
| Со | <1.0 | | | |
| Cr | 17 | 21 | | |
| Ni | 50 | 55 | | |
| Мо | 2.8 3.3 | | | |
| Ti | 0.6 1.25 | | | |
| Al | 0.3 | 0.7 | | |
| Nb | 4.7 | 5.5 | | |
| Fe | Balance | | | |



Process information

| MPRINT | | |
|-----------------------|--|--|
| 2.4668/Alloy 718 40µm | | |
| Netfabb | | |
| MSUPPLY 2.4668 | | |
| 40μm | | |
| X-Lip | | |
| Nitrogen | | |
| 80µm | | |
| | | |



Physical and Mechanical Properties

In annealed condition the tensile strength of the material is ca. 1030 N/mm². But based on the heat treatment method used, the tensile strength can increase to ca. 1450 N/mm². The material has an excellent creep rupture strength and can retain most of the properties at elevated temperatures. The operating temperature range of the material ranges from cryogenic temperature to 700°C. The material also has excellent oxidation resistance up to 1000°C.

Physical properties

| Defects | Result | | |
|--------------------|--------|--|--|
| Average defect (%) | <0.1 | | |

Surface quality (measured along the z-axis)

| As built | Ra [µm] | 3 |
|----------|---------|----|
| | Rz [µm] | 15 |
| Blasted | Ra [µm] | 2 |
| | Rz [μm] | 12 |

Mechanical properties ISO6892-1

| Vertical | Yield strength Rp0.2 [MPa] | Tensile strength Rm [MPa] | Elongation at break A [%] | Reduction of area Z [%] |
|--------------------------------|-------------------------------|------------------------------|------------------------------|-------------------------|
| Average | 588 | 952 | 37 | 54 |
| Absolute Standard Deviation | 17 | 3 | 1 | 3 |
| Relative Standard Deviation | 3 | 0.3 | 3 | 6 |



